



Improving the Rod-Penetration Algorithm for Tomorrow's Armors

by Steven B. Segletes, Rick Grote, and John Polesne

ARL-RP-23

June 2001

A reprint from *Proceedings of the 22nd Army Science Conference*, pp. 66-71, Baltimore, MD, 11-13 December 2000.

Approved for public release; distribution is unlimited.

20010628 054

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-RP-23

June 2001

Improving the Rod-Penetration Algorithm for Tomorrow's Armors

Steven B. Segletes

Weapons and Materials Research Directorate, ARL

Rick Grote and John Polesne

Survivability/Lethality Analysis Directorate, ARL

A reprint from *Proceedings of the 22nd Army Science Conference*, pp. 66-71, Baltimore, MD,
11-13 December 2000.

Approved for public release; distribution is unlimited.

Abstract

The performance of the respected Frank-Zook penetration algorithm (Zook, J. A., Frank, K., and Silsby, G. F., "Terminal Ballistics Test and Analysis Guidelines for the Penetration Mechanics Branch," BRL-MR-3960, January 1992) is examined in light of an anticipated class of target technologies involving laminated targets whose layers are thin relative to the projectile diameter. This class of target designs encompasses multifunctional integral armors and, in the limiting case, armors incorporating functionally-graded materials. Such armor classes represent potential candidates for the Army's Future Combat System. The ability to effectively model the ballistic response of advanced armors is paramount to accurately assessing system lethality and vulnerability for future weapon systems and platforms.

IMPROVING THE ROD-PENETRATION ALGORITHM FOR TOMORROW'S ARMORS

Steven B. Segletes*, Rick Grote, John Polesne
U.S. Army Research Laboratory
Aberdeen Proving Ground, Maryland 21005

ABSTRACT

The performance of the respected Frank-Zook penetration algorithm (Zook *et al.*, 1992) is examined in light of an anticipated class of target technologies involving laminated targets whose layers are thin relative to the projectile diameter. This class of target designs encompasses multifunctional integral armors and, in the limiting case, armors incorporating functionally-graded materials. Such armor classes represent potential candidates for the Army's Future Combat System. The ability to effectively model the ballistic response of advanced armors is paramount to accurately assessing system lethality and vulnerability for future weapon systems and platforms.

1. MOTIVATION

The Survivability/Lethality Analysis Directorate (SLAD) and the Weapons and Materials Research Directorate (WMRD) of the Army Research Laboratory (ARL) are jointly working in the area of Target Interaction Lethality/Vulnerability (TILV) – Ballistic Damage of Advanced Material and Armor Systems. SLAD is upgrading their MUVES S2 suite of vulnerability/lethality models (Hanes *et al.*, 1988) as part of the TILV program. Vulnerability/lethality models are being constantly challenged by new, sophisticated and complicated armor technologies. Although there can be tremendous variations in these new technological advances, they can be generalized under the following categories: spaced and layered solutions, reactive and passive appliques, ceramic solutions, impact-energy absorption techniques, advanced metals and matrix geometries, functionally graded materials (FGMs), electromagnetic techniques, and polymer solutions (transparent armors). These new armor design technologies are surfacing as potential candidates for both foreign and U.S. ground/air combat systems. The U.S. Army's Future Combat System may include many of these armor classes.

To understand the implications of these new ballistic-protection technologies before they become fielded on future systems, this collaborative effort has been established to develop a physically-based penetration model that is suitable for implementation into the MUVES S2 suite of models. A "building block" approach has been adopted wherein the currently utilized penetration equations are first examined and refined to better estimate the ballistic performance of laminated spaced armor solutions versus kinetic energy projectiles, with an eye towards eventually

developing penetration equations to accurately estimate the ballistic response of FGMs.

Traditional penetration methodologies, like those of Tate (1967) and Alekseevskii (1966), were developed for rods penetrating idealized semi-infinite target blocks. As such, target resistance variations along the shotline were not an issue. Later analyses (Wright and Frank, 1988; Tate, 1986; Walker and Anderson, 1995) showed that the property of target resistance represents an integral of stresses throughout the plastic zone in the target, ahead of the rod/target interface. In the course of penetration, when this plastic zone crosses the interface between two adjacent target plies, one may infer that the local target properties should be properly composed of material properties from both of the entrained plies. In this manner, the transition of "effective" material properties penetrating from one target ply into the next should be continuous, rather than discrete.

The Frank-Zook (FZ) penetration algorithm (Zook *et al.*, 1992), used widely within the ARL for both terminal ballistic evaluation and vulnerability assessment, considers this interply transition process. However, since it was developed when long rods and relatively thick target elements represented the prevalent engagement scenario, the FZ algorithm computes this transition effect a single target element at a time (*i.e.*, it only senses one target element in advance).

The FZ algorithm can accurately sense and respond to the situation where, for example, the penetration channel proceeds from a weak target element into a strong target element. The effective resistance offered by the target would gradually and smoothly transition from the weak value, just reaching the strong value of resistance as the penetrator/target interface reaches the strong target element. If a rod of diameter D is penetrating target element i , the influence of target element $i+1$ upon the effective target resistance \bar{H} is evaluated by the FZ model as

$$\bar{H} = H_i + (H_{i+1} - H_i) e^{-2T_{res}/3D}, \quad (1)$$

where the H_i are the target-element component resistances, and T_{res} is the residual, normal thickness of target element i yet to be penetrated. In the absence of this modeling enhancement, the transition in target resistance would be unrealistically abrupt.

However, implementing this realistic enhancement within the FZ algorithm is accomplished only a single interface at a time (*i.e.*, target elements $i+2$, *etc.* do not affect

the effective resistance). Thus, if the finite target volume contributing to the target resistance realistically entrained several target/target interfaces, the FZ algorithm would only account for the one closest to the penetrator/target interface. Such a situation can realistically arise in several situations. One is where there exists a target composed of elements that are thin compared to the penetrator diameter, possibly as in the case of targets designed for small- and medium-caliber threats. In this case, the plasticity zone will entrain not two, but a larger number of target element layers simultaneously (Fig. 1). For such targets, the FZ algorithm will be ill-suited to model the transition of "effective" target resistance and density along the shotline. Though the problem can be quite severe when the target-layer thickness is a fraction of the projectile diameter, the effect is still evident to a much lesser extent, even as the target-element thickness is increased to several projectile diameters.

Another example in which several target/target interfaces could be entrained in the zone of target material contributing to target resistance is when a target element is barely clipped by the penetrator shotline. This latter situation can arise even if the individual target elements are otherwise thick. And since, from the point of view of a statistical vulnerability computation, the process of selecting and calculating penetrator shotline geometries is fully automated, the vulnerability analyst has little or no control in preventing very thin target elements from arising along a given shotline geometry, even for large-caliber targets.

2. DISCUSSION

A remedy to these types of problems is offered and accomplished by a novel adaptation of elements from a model by Walker and Anderson (1995) into the FZ framework. In so doing, the target's material properties and nonsteady-kinematic properties are dynamically composed via an integration through the plastic zone in the target, ahead of the rod/target interface. Though the Walker-Anderson model does not even address the issue of multilayer targets, the assumed flow field kinematics of their model provide enough information to isolate and dynamically calculate an integrated contribution from each layer in a given laminate target towards the aggregated or "effective" target properties.




Fig. 1. Plastically entrained elements contribute to "effective" target properties, e.g., resistance $H = H(i, j, k, m)$.

This integration is accomplished by using the extended Bernoulli equation (Segletes and Walters, 1999) to yield the relation that governs the rod/target interaction. The equation includes aggregated terms summed from all of the layers of target material entrained in the plastic zone:

$$\left(k_p - \frac{1}{2} \frac{\dot{s}}{L}\right) \rho_p (V - U)^2 + Y - \frac{\rho_p s}{2} (\dot{V} + \dot{U}) = k_r \bar{\rho} U^2 + \bar{H} + X_U \frac{\dot{U}}{U} + X_\alpha \frac{\dot{\alpha}}{\alpha} + X_R \frac{\dot{R}}{R}, \quad (2)$$

where k_r , ρ_p , Y , V , and s are the shape factor, density, strength/resistance, velocity, and plastic-zone extent in the rod of length L and diameter D , while k_r , $\bar{\rho}$, \bar{H} , U and α are the corresponding values for the target interface. The X terms are nonsteady-influence terms defined below. Namely, for a plastic zone of thickness $(\alpha - 1)$ times the crater radius R , spanning across target elements $i = m$ to n , of density ρ_{Ti} , where the $(i-1) \rightarrow i$ intra-target interface is positioned at $z = (\beta_i - 1)R$ with respect to the rod/target interface (with $\beta_m = 1$, $\beta_{n+1} = \alpha$), the following generalized expressions for the target parameters are obtained:

$$\bar{\rho} = \sum_{i=m}^n \frac{\alpha^4}{(\alpha^2 - 1)^2} \left[\frac{(2\beta_i^2 - 1)}{\beta_i^4} - \frac{(2\beta_{i+1}^2 - 1)}{\beta_{i+1}^4} \right] \rho_{Ti}, \quad (3)$$

$$\bar{H} = \sum_{i=m}^n \frac{\ln(\beta_{i+1}/\beta_i)}{\ln(\alpha)} H_i, \quad (4)$$

$$X_U = UR \sum_{i=m}^n \frac{\rho_{Ti}}{(\alpha^2 - 1)} \left[\frac{(\beta_i^2 + \alpha^2)}{\beta_i} - \frac{(\beta_{i+1}^2 + \alpha^2)}{\beta_{i+1}} \right], \quad (5)$$

$$X_\alpha = UR \sum_{i=m}^n \frac{2\rho_{Ti}\alpha^2}{(\alpha^2 - 1)^2} \left[\frac{(\beta_{i+1}^2 + 1)}{\beta_{i+1}} - \frac{(\beta_i^2 + 1)}{\beta_i} \right], \text{ and } (6)$$

$$X_R = UR \sum_{i=m}^n \frac{\rho_{Ti}\alpha^2}{(\alpha^2 - 1)} \left[\frac{(2\beta_i - 1)}{\beta_i^2} - \frac{(2\beta_{i+1} - 1)}{\beta_{i+1}^2} \right]. \quad (7)$$

These results reduce to those of Walker and Anderson (1995) for the case of monolithic targets, wherein $m = n = 1$, and the limits on β correspond to the extent of the plastic zone as $\beta_1 = 1$, and $\beta_2 = \alpha$.

3. RESULTS

A test series was conducted by personnel at ARL's Experimental Facility 110, using the 14.5 mm B32 armor-piercing projectile, weighing 63.5 g and consisting of a 53 mm, 41 g hardened-steel (Rc 65) core surrounded by a brass jacket (Fig. 2). The gun-breech powder loading was altered to systematically vary the projectile velocity.

The projectile was modeled as a 63.5 g homogeneous steel slug, 66.5 mm long \times 12.45 mm diameter, equaling the overall length and mass of the B32 projectile. Because the sharpened B32 core penetrates as a rigid body, the shape factor, k_r , of the target flow was set to 0.15 rather than 0.5, reflecting the reduced momentum transfer imparted to a sharpened body as compared to the stagnation flow of blunt-

body penetration. This revised k_T value is based on the fact that the force required to turn an inviscid flow through an angle of θ is proportional to $(1 - \cos\theta)$. This suggests that k_T take on the value $1/2 (1 - \cos\delta)$, where δ is the half-angle of the rigid-projectile nose, approximately 45° for the tip of the B32 core. It is important to note that without accounting for the influence of both the brass-jacket mass and the pointed aspect of the rigid core, the calibration tests of B32 penetration into "semi-infinite" 5083 aluminum underestimated the penetration, as shown in Fig. 3.

Into semi-infinite and finite-plate targets, the FZ and revised models both perform well, as anticipated and shown in Fig. 4. The material modeling parameters for all calculations are given in Table 1. Values for target resistance were selected to fit the data, but are compatible with various analytical estimation techniques. Plastic-zone extent values will be subsequently discussed. The slight discrepancy between models was caused by introducing the integrated (*i.e.*, "effective") and nonsteady terms of equation (2) in the revised modeling approach.

However, to appreciate the distinction between the original and revised methodology, consider the 23 mm plate of 5083 aluminum that composed the target of Fig. 4b, and augment the target by adding a 0.8 mm mild-steel backing plate to the rear of the aluminum plate. Fig. 5 presents the data as well as modeling predictions, including those for the original configuration without the steel backing. The addition of this thin plate should have a minimal effect on the ballistic resistance of the target, which is indeed reflected in the data. And while the revised modeling

Table 1. Material Modeling Parameters*			
Projectile Material	ρ_p (kg/m ³)	Y (GPa)	
Steel (Rc65)	7850	4.46	
Target Material	ρ_t (kg/m ³)	H (GPa)	Plastic Zone Extent PZE/D
5083 Al. (BHN 103)	2700	1.92	5.1
Mild Steel (BHN 93)	7850	2.09	3.5
HHAl (BHN 500)	7850	6.15	3.5
Acrylic	1190	0.62	3.5

*Target rear surfaces modeled with 0.5 GPa spall strength




Fig. 2. The B32 armor-piercing core and projectile.

corroborates this minimal influence, the original model improperly accentuates the effect. However, it is not the resistance of steel backing that in and of itself produces this effect in the original model. Rather, the error is introduced while penetrating the aluminum plate, since the rod is at that moment unaware that the target rear surface exists. As such, it is the failure to perceive incipient breakout (and the associated diminution of resistance) while penetrating the aluminum that results in the underestimation of residual velocity, V_r , by the original model.






Fig. 3. Penetration of B32 into 5083 aluminum using various modeling assumptions.



(a)



(b)

Fig. 4. Comparison of FZ model and revised model for B32 against (a) semi-infinite 5083 aluminum, and (b) 23 mm plate of 5083 aluminum at 0° obliquity.

As a second example, consider the same 23 mm target of 5083 aluminum, this time backed by a 9.6 mm high-hard armor (HHA) plate. Even though the HHA element is not nearly so thin as the mild-steel backing of the previous example, it is still thin enough, relative to the 12.45 mm projectile core, for the original model to suffer the identical problem for the same reason, as shown in Fig. 6. For the original model to better match the data, the HHA target resistance would have to be lowered nearly 40% to an artificially low value of 3.75 GPa.

To remove any lingering doubt that the root of the original model's problem arises from its treatment of subsequent target elements only one at a time, consider the aluminum/HHA target under discussion with a 2.8 mm acrylic interply between the aluminum and HHA. While it may be surmised that the interply's contribution to the target's ballistic resistance should be minimal, that influence should nonetheless be a trend of slight strengthening. Thus, the residual-velocity curves of Fig. 7 depict both the inconsistency that can occur when the model can only sense one advance target-element at a time, as well

as the correction offered by the revised modeling. Contrary to both expectation and data trend, adding the acrylic interply significantly weakens the overall target resistance, according to the original methodology. The cause for this inconsistent behavior may be understood from Fig. 8, which portrays the target resistance as a function of location through the target.

3.1 Analysis of Model Parameter Influence

In particular, Fig. 8 depicts how the original model perceives these two target configurations quite differently. For the baseline case without the interply (Fig. 8a), the FZ algorithm properly senses the influence of the strong HHA plate while penetrating the 5083 aluminum, but fails to detect the rear surface of the target prior to actually entering the HHA element. Thus, the resistance undergoes a large and instantaneous correction upon entering the HHA plate, since the target free surface then becomes recognized. Because of the overestimated resistance while penetrating the aluminum, the original algorithm underpredicts the residual velocity (V_r) exiting the baseline target. Once in the HHA plate, only one interface (*i.e.*, the rear surface) is entrained in the target's plastic zone. Consequently, the two models exhibit nearly identical behavior at this point; the small differences are attributable to the difference between the FZ formulation for resistance given by eqn (1) and the revised formulation given by eqn (4).

For the test case containing the acrylic interply (Fig. 8b), the influence of the hard HHA plate is not sensed by the FZ algorithm while penetrating the 5083 element until the acrylic is actually reached. Rather, the 5083 plate senses only the weak acrylic interply. As such, the original algorithm underestimates the target resistance in the aluminum and overpredicts the residual velocity exiting the test-case target.

In contrast, the revised algorithm, by simultaneously accounting for all the relevant target elements and free




Fig. 5. Comparison of FZ model and revised model for B32 against 23 mm plate of 5083 aluminum with and without 0.8 mm mild-steel backplate.




Fig. 6. Comparison of original and revised models for B32 vs. target consisting of 23 mm 5083 aluminum plus 9.6 mm HHA.




Fig. 7. Effect of 2.8 mm interply layer of acrylic on original and revised models for B32 vs. target consisting of a 23 mm 5083 aluminum plus 9.6 mm HHA baseline.

surfaces in proportion to their actual influence, properly captures both the magnitude and sense of the ballistic trend. While the original formulation can experience large instantaneous jumps in target resistance [recall that one purpose of eqn (1) was to help avoid this occurrence], even the revised formulation seen in Fig. 8 experiences a small instantaneous jump of around 0.35 GPa at the rear surface of the 5083 target element. The source of this jump is the difference in plastic-zone extent modeled for the aluminum, compared with that for the other target materials.

Before discussing the influence of the plastic-zone-extent parameter on results of the revised model, the magnitude of this target-resistance jump represents the error introduced by assuming that the flow field in the plastic zone obeys the spatially hemispherical function selected by Walker and Anderson (1995), even as that flow field extends across material interfaces. The use of this flow-field assumption across material interfaces is a valid criticism of the revised formulation, reflecting the fact that the actual plastic zone shape ahead of the rod/target interface will not, in reality, remain hemispherical across an

interface of dissimilar materials. However, despite this criticism, the assumption is nonetheless a significant improvement over the original formulation in this regard, as reflected in Fig. 8. A future improvement to the revised model can be achieved by transitioning the plastic-zone extent gradually, as an interface is approached, rather than abruptly, as is currently done. With such an improvement, the target resistance would always remain continuous with position.

As listed in Table 1, the plastic-zone extent (*PZE*) in the 5083 aluminum was taken as 5.1 projectile diameters, compared with a value of 3.5 for the other target materials. While this alteration was done to improve the fit to data, an analytical method for estimating this parameter from material properties is planned for future work. This alteration to the aluminum's plastic-zone extent provides an opportunity to study this parameter's effect on the revised model. The influence of an alteration in aluminum's *PZE*, from a value of 5.1 to 3.5 on the revised-model predictions, is shown in Table 2 for data from various figures. And while the impact on the model predictions of Fig. 7 may seem large, much of that is attributable directly to the fact that the low-velocity data is very close to the ballistic limit, where small model changes of any type can have a large-percentage influence on the residual velocity. For the data in Fig. 7, the influence of the cited change in *PZE* drops to 7% for striking speeds above 700 m/s, and to under 2% by 1000 m/s striking speed. It appears that model results, at least in the cases studied to date, are not overly sensitive to the selection of this parameter.

4. CONCLUSIONS

When investigating the ability of the current FZ penetration algorithm to predict the ballistic performance of targets comprising thin (or functionally-graded) elements, a deficiency was noted arising from the algorithm's ability to examine the influence of only one leading target element at a time. A remedy has been offered that incorporates elements of a model by Walker and Anderson (1995) into the existing FZ framework. Both models were compared against data for the 14.5 mm B32 penetrator against several target configurations designed to probe the perceived algorithm deficiency. The revised model compares well to data, for several different test cases, offering notable improvement over the original methodology for the cases




Fig. 8. Target resistance vs. location for target consisting of 23 mm 5083 aluminum plus 9.6mm HHA, (a) without interply, (b) with 2.8 mm acrylic acrylic interply.

Table 2. Influence of Plastic-Zone-Extent Variation

On What	Fig.	Influence of PZE variation from 5.1 to $3.5 \times D$
Penetration	3	< 0.5%.
Residual Velocity	5	< 2%
Residual Velocity	7	~ 30% at $V_s = 580$ m/s
Residual Velocity	7	~ 7% at $V_s = 700$ m/s
Residual Velocity	7	< 2% at $V_s = 1000$ m/s

studied. These modeling remedies and enhancements are being considered for incorporation into the Army Research Laboratory's MUVES code, as part of ARL's vulnerability/lethality calculation methodology.

ACKNOWLEDGMENTS

The authors would like to thank all the crewmembers of ARL's Experimental Facility 110, most especially Eleanor Deal, Dick English, and Bernie McKay, for executing the testing program that produced the experimental results presented in this report.

REFERENCES

Alekseevskii, V. P., *Comb. Expl. and Shock Waves*, Vol 2, pp. 63-66, 1966.

Hanes, P.J., Murray, K. R., Gwyn, D. A., and Polak, H. R., "An Overview and Status Report of MUVES (Modular UNIX-Based Vulnerability Estimation Suite)," BRL-MR-3679, July, 1988.

Segletes, S. B. and Walters, W. P., "A Note on the Application of the Extended Bernoulli Equation," ARL-TR-1895, February 1999.

Tate, A., *J. Mech. Phys. Solids*, Vol 15, pp. 387-399, 1967.

Tate, A., *Int. J. Mech. Sci.*, Vol 28, No. 8, pp. 535-547, 1986.

Walker, J. D. and Anderson, C. E. Jr., *Int. J. Impact Engng.*, Vol 16, No.1, pp. 19-48, 1995.

Wright, T. W., and Frank, K., "Approaches to Penetration Problems," BRL-TR-2957, December 1988.

Zook, J. A., Frank, K., and Silsby, G. F., "Terminal Ballistics Test and Analysis Guidelines for the Penetration Mechanics Branch," BRL-MR-3960, January 1992.

NO. OF
COPIES ORGANIZATION

2 DEFENSE TECHNICAL
INFORMATION CENTER
DTIC OCA
8725 JOHN J KINGMAN RD
STE 0944
FT BELVOIR VA 22060-6218

1 HQDA
DAMO FDT
400 ARMY PENTAGON
WASHINGTON DC 20310-0460

1 OSD
OUSD(A&T)/ODDR&E(R)
DR R J TREW
3800 DEFENSE PENTAGON
WASHINGTON DC 20301-3800

1 COMMANDING GENERAL
US ARMY MATERIEL CMD
AMCRDA TF
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

1 INST FOR ADVNCD TCHNLGY
THE UNIV OF TEXAS AT AUSTIN
3925 W BRAKER LN STE 400
AUSTIN TX 78759-5316

1 DARPA
SPECIAL PROJECTS OFFICE
J CARLINI
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

1 US MILITARY ACADEMY
MATH SCI CTR EXCELLENCE
MADN MATH
MAJ HUBER
THAYER HALL
WEST POINT NY 10996-1786

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL D
DR D SMITH
2800 POWDER MILL RD
ADELPHI MD 20783-1197

NO. OF
COPIES ORGANIZATION

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CI AI R
2800 POWDER MILL RD
ADELPHI MD 20783-1197

3 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CI LL
2800 POWDER MILL RD
ADELPHI MD 20783-1197

3 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CI IS T
2800 POWDER MILL RD
ADELPHI MD 20783-1197

ABERDEEN PROVING GROUND

2 DIR USARL
AMSRL CI LP (BLDG 305)

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	US ARMY DUSA OPS RSCH D WILLARD 102 ARMY PENTAGON WASHINGTON DC 20310-0102
5	DEFENSE NUCLEAR AGENCY MAJ J LYON CDR K W HUNTER T FREDERICKSON R J LAWRENCE SPSP K KIBONG 6801 TELEGRAPH RD ALEXANDRIA VA 22310-3398
3	COMMANDER US ARMY ARDEC AMSTA AR FSA E W P DUNN J PEARSON E BAKER PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR CCH V M D NICOLICH PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC E ANDRICOPOULOS PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER USA STRATEGIC DEFNS CMD CSSD H LL T CROWLES HUNTSVILLE AL 35807-3801
3	COMMANDER US ARMY AVIATION & MISSILE COMMAND AMSAM RD PS WF S HILL D LOVELACE M SCHEXNAYDER REDSTONE ARSENAL AL 35898-5247

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	MIS DEFNS & SPACE TECHNOLOGY CSSD SD T K H JORDAN PO BOX 1500 HUNTSVILLE AL 34807-3801
3	COMMANDER US ARMY RESEARCH OFFICE K IYER J BAILEY S F DAVIS PO BOX 12211 RESEARCH TRIANGLE PARK NC 27709-2211
1	NAVAL AIR WARFARE CTR S A FINNEGAN BOX 1018 RIDGECREST CA 93556
4	COMMANDER NAVAL WEAPONS CENTER N FASIG CODE 3261 T T YEE CODE 3263 D THOMPSON CODE 3268 W J MCCARTER CODE 6214 CHINA LAKE CA 93555
12	COMMANDER NAVAL SURFACE WARFARE CTR DAHLGREN DIVISION H CHEN D L DICKINSON CODE G24 C R ELLINGTON C R GARRETT CODE G22 W HOLT CODE G22 W E HOYE G22 R MCKEOWN J M NELSON M J SILL CODE H11 W J STROTHER A B WARDLAW JR L F WILLIAMS CODE G33 17320 DAHLGREN RD DAHLGREN VA 22448

<u>NO. OF</u> <u>COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF</u> <u>COPIES</u>	<u>ORGANIZATION</u>
8	AIR FORCE RESEARCH LAB MUNITIONS DIRECTORATE BLDG 13 MNAC W COOK MNAC M NIXON MNM MNMW J FOSTER MNMW J HOUSE MNMI B MILLIGAN MNAL D BRUBAKER MNAL B PATTERSON 101 W EGLIN BLVD EGLIN AFB FL 32542-6810	30	SANDIA NATIONAL LABS ATTN MAIL SERVICES MS-0100 J ANG MS0310 P YARRINGTON MS0310 W TEDESCHI MS0479 B LEVIN MS0706 A ROBINSON MS0819 T TRUCANO MS0819 P TAYLOR MS0820 R BRANNON MS0820 M KIPP MS0820 D CRAWFORD MS0820 L CHHABILDAS MS0821 P STANTON MS0821 J M MCGLAUN MS0835 E S HERTEL JR MS0836 L N KMETYK MS0980 R REEDER MS0980 J SOUTHWARD MS0980 R LAFARGE MS0986 R TACHAU MS1156 M FURNISH MS1168 M FORRESTAL MS1174 W REINHART MS1181 D HAYES MS1181 J ASAY MS1181 E W REECE MS1185 D P KELLY MS1185 C HALL MS1209 J COREY MS1217 C HILLS MS1411 M VIGIL MS1454 PO BOX 5800 ALBUQUERQUE NM 87185-0100
1	USAF PHILLIPS LABORATORY VTSI R ROYBAL KIRTLAND AFB NM 87117-7345		
2	USAF PHILLIPS LABORATORY PL WSCD F ALLAHDAI PV VTA D SPENCER 3550 ABERDEEN AVE SE KIRTLAND AFB NM 87117-5776		
1	AFIT ENC D A FULK WRIGHT PATTERSON AFB OH 45433		
1	FED BUREAU OF INVESTIGATION FBI LAB - EXPLOSIVES UNIT M G LEONE 935 PENNSYLVANIA AVE NW WASHINGTON DC 20535		
6	LOS ALAMOS NATIONAL LAB L HULL MS A133 J V REPA MS A133 J WALTER MS C305 E J CHAPYAK MS F664 P HOWE MS P915 J KENNEDY MS P915 PO BOX 1663 LOS ALAMOS NM 87545	4	DIRECTOR LLNL MS L35 R E TIPTON D BAUM M MURPHY T MCABEE PO BOX 808 LIVERMORE CA 94550

NO. OF
COPIES ORGANIZATION

7 DIRECTOR
LLNL
MS L122
R PIERCE
R ROSINKY
O J ALFORD
D STEWART
T VIDLAK
B R BOWMAN
W DIXON
PO BOX 808
LIVERMORE CA 94550

2 DIRECTOR
LLNL
MS L125
D R FAUX
N W KLINO
PO BOX 808
LIVERMORE CA 94550

1 DIRECTOR
LLNL
R BARKER L159
PO BOX 808
LIVERMORE CA 94550

3 DIRECTOR
LLNL
MS L163
M FINGER
R PERRET
W SHOTTS
PO BOX 808
LIVERMORE CA 94550

3 DIRECTOR
LLNL
MS L178
H KRUGER
G POMYKAL
M GERASSIMENKO
PO BOX 808
LIVERMORE CA 94550

2 DIRECTOR
LLNL
MS L180
G SIMONSON
A SPERO
PO BOX 808
LIVERMORE CA 94550

NO. OF
COPIES ORGANIZATION

1 DIRECTOR
LLNL
F A HANDLER L182
PO BOX 808
LIVERMORE CA 94550

1 DIRECTOR
LLNL
MS L282
W TAO
PO BOX 808
LIVERMORE CA 94550

2 DIRECTOR
LLNL
MS L290
A HOLT
J E REAUGH
PO BOX 808
LIVERMORE CA 94550

1 DIRECTOR
LLNL
S G COCHRAN L389
PO BOX 808
LIVERMORE CA 94550

2 DIRECTOR
LLNL
MS L495
D GAVEL
J HUNTER
PO BOX 808
LIVERMORE CA 94550

1 DIRECTOR
LLNL
R M KUKLO L874
PO BOX 808
LIVERMORE CA 94550

3 DIRECTOR
LLNL
G W REPP
M SHANNON
BMDO R M HALL
PO BOX 808
LIVERMORE CA 94550

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
4	ENERGETIC MATERIALS RSCH TESTING CTR NEW MEXICO TECH D J CHAVEZ L LIBERSKY F SANDSTROM M STANLEY CAMPUS STATION SOCORRO NM 87801	1	GEORGIA INST OF TECHNOLOGY COMPUTATIONAL MODELING CTR S ATLURI ATLANTA GA 30332-0356
3	NASA JOHNSON SPACE CENTER E CHRISTIANSEN J L CREWS F HORZ MAIL CODE SN3 2101 NASA RD 1 HOUSTON TX 77058	1	GEORGIA INST OF TECHNOLOGY SCHOOL OF MATL SCIENCE & ENG K LOGAN ATLANTA GA 30332-0245
1	APPLIED RESEARCH LAB J A COOK 10000 BURNETT ROAD AUSTIN TX 78758	1	IOWA STATE UNIVERSITY DEPT PHYSICS AND ASTRONOMY J ROSE 34 PHYSICS AMES IA 50011
5	JET PROPULSION LABORATORY IMPACT PHYSICS GROUP Z SEKANINA P WEISSMAN B WEST J ZWISSLER M ADAMS 4800 OAK GROVE DR PASADENA CA 91109	1	JOHNS HOPKINS UNIVERSITY MAT SCI & ENGN G DEPT M LI 102 MARYLAND HALL 3400 N CHARLES ST BALTIMORE MD 21218-2689
2	CALTECH J SHEPHERD MS 105 50 A P INGERSOLL MS 170 25 1201 E CALIFORNIA BLVD PASADENA CA 91125	5	JOHNS HOPKINS UNIVERSITY APPLIED PHYSICS LAB T R BETZER A R EATON R H KEITH D K PACE R L WEST JOHNS HOPKINS ROAD LAUREL MD 20723
1	CALTECH G ORTON MS 169 237 4800 OAK GROVE DR PASADENA CA 91007	1	LOUISIANA STATE UNIVERSITY R W COURTER 948 WYLIE DR BATON ROUGE LA 70808
1	DREXEL UNIVERSITY MEM DEPT 32ND & CHESTNUT ST PHILADELPHIA PA 19104	1	NC STATE UNIVERSITY Y HORIE RALEIGH NC 27695-7908
		4	SOUTHWEST RESEARCH INST C ANDERSON S A MULLIN J RIEGEL J WALKER PO DRAWER 28510 SAN ANTONIO TX 78228-0510

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	SUNY STONY BROOK DEPT APPL MATH & STAT J GLIMM STONY BROOK NY 11794
1	UC BERKELEY MECHANICAL ENG DEPT GRADUATE OFFICE K LI BERKELEY CA 94720
1	UC DAVIS INST OF THEORETICAL DYNAMICS E G PUCKETT DAVIS CA 95616
2	UC SAN DIEGO DEPT APPL MECH & ENGR SVCS R011 S NEMAT NASSER M MEYERS LA JOLLA CA 92093-0411
2	UNIV OF AL HUNTSVILLE AEROPHYSICS RSCH CTR G HOUGH D J LIQUORNIK PO BOX 999 HUNTSVILLE AL 35899
1	UNIV OF AL HUNTSVILLE MECH ENGRNG DEPT W P SCHONBERG HUNTSVILLE AL 35899
2	UNIVERSITY OF DAYTON RESEARCH INSTITUTE N BRAR A PIEKUTOWSKI 300 COLLEGE PARK DAYTON OH 45469-0182
3	UNIVERSITY OF DELAWARE DEPT OF MECHANICAL ENG J GILLESPIE J VINSON D WILKINS NEWARK DE 19716

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	UNIVERSITY OF PENNSYLVANIA P A HEINEY DEPT OF PHYSICS & ASTRONOMY 209 SOUTH 33RD ST PHILADELPHIA PA 19104
1	UNIVERSITY OF PUERTO RICO DEPT CHEMICAL ENGINEERING L A ESTEVEZ MAYAGUEZ PR 00681-5000
1	UNIVERSITY OF TEXAS DEPT OF MECHANICAL ENG E P FAHRENTHOLD AUSTIN TX 78712
1	VIRGINIA POLYTECHNIC INST COLLEGE OF ENGINEERING DEPT ENG SCI & MECHANICS R C BATRA BLACKSBURG VA 24061-0219
2	AEROJET J CARLEONE S KEY PO BOX 13222 SACRAMENTO CA 95813-6000
2	AEROJET ORDNANCE P WOLF G PADGETT 1100 BULLOCH BLVD SOCORRO NM 87801
3	ALLIANT TECHSYSTEMS INC R STRYK G R JOHNSON MN11 1614 P SWENSON MN11 2720 600 SECOND ST NE HOPKINS MN 55343
1	M L ALME 2180 LOMA LINDA DR LOS ALAMOS NM 87544-2769
1	APPLIED RESEARCH ASSOC INC J D YATTEAU 5941 S MIDDLEFIELD RD SUITE 100 LITTLETON CO 80123

<u>NO. OF</u> <u>COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF</u> <u>COPIES</u>	<u>ORGANIZATION</u>
2	APPLIED RESEARCH ASSOC INC D GRADY F MAESTAS SUITE A220 4300 SAN MATEO BLVD NE ALBUQUERQUE NM 87110	3	DOW CHEMICAL INC ORDNANCE SYSTEMS C HANEY A HART B RAFANIELLO 800 BUILDING MIDLAND MI 48667
1	APPLIED RESEARCH LABS T M KIEHNE PO BOX 8029 AUSTIN TX 78713-8029	3	DYNA EAST CORP P C CHOU R CICCARELLI W FLIS 3620 HORIZON DRIVE KING OF PRUSSIA PA 19406
1	ATA ASSOCIATES W ISBELL PO BOX 6570 SANTA BARBARA CA 93111	3	DYNASEN J CHAREST M CHAREST M LILLY 20 ARNOLD PL GOLETA CA 93117
1	BATTELLE R M DUGAS 7501 S MEMORIAL PKY STE 101 HUNTSVILLE AL 35802-2258	1	R J EICHELBERGER 409 W CATHERINE ST BEL AIR MD 21014-3613
1	BOEING HOUSTON SPACE STN R F GRAVES BOX 58747 HOUSTON TX 77258	1	ELORET INSTITUTE D W BOGDANOFF MS 230 2 NASA AMES RESEARCH CENTER MOFFETT FIELD CA 94035
1	BRIGS CO J E BACKOFEN 2668 PETERSBOROUGH ST HERNDON VA 20171-2443	1	EXPLOSIVE TECHNOLOGY M L KNAEBEL PO BOX KK FAIRFIELD CA 94533
1	COMPUTATIONAL MECHANICS CONSULTANTS J A ZUKAS PO BOX 11314 BALTIMORE MD 21239-0314	1	GB TECH LOCKHEED J LAUGHMAN 2200 SPACE PARK SUITE 400 HOUSTON TX 77258
1	CYPRESS INTERNATIONAL A CAPONECCHI 1201 E ABINGDON DR ALEXANDRIA VA 22314	2	GB TECH LOCKHEED L BORREGO C23C J FALCON JR C23C 2400 NASA ROAD 1 HOUSTON TX 77058
1	DESKIN RESEARCH GROUP INC E COLLINS 2270 AGNEW RD SANTA CLARA CA 95054		

NO. OF COPIES	ORGANIZATION
6	GDLS 38500 MOUND RD W BURKE MZ436 21 24 G CAMPBELL MZ436 30 44 D DEBUSSCHER MZ436 20 29 J ERIDON MZ436 21 24 W HERMAN MZ 435 01 24 S PENTESCU MZ436 21 24 STERLING HTS MI 48310-3200
1	GENERAL RESEARCH CORP T MENNA PO BOX 6770 SANTA BARBARA CA 93160-6770
1	RAYTHEON MSL SYS CO T STURGEON BLDG 805 M/S D4 PO BOX 11337 TUCSON AZ 85734-1337
5	INST FOR ADVANCED TECH S J BLESS J CAZAMIAS J DAVIS H D FAIR D LITTLEFIELD 3925 W BRAKER LN SUITE 400 AUSTIN TX 78759-5316
1	INTERNATIONAL RSRCH ASSOC D L ORPHAL 4450 BLACK AVE PLEASANTON CA 94566
1	ITT SCIENCES AND SYSTEMS J WILBECK 600 BLVD SOUTH SUITE 208 HUNTSVILLE AL 35802
1	R JAMESON 624 ROWE DR ABERDEEN MD 21001
1	KAMAN SCIENCES CORP D L JONES 2560 HUNTINGTON AVE STE 200 ALEXANDRIA VA 22303

NO. OF COPIES	ORGANIZATION
7	KAMAN SCIENCES CORP J ELDER R P HENDERSON D A PYLES F R SAVAGE J A SUMMERS T W MOORE T YEM 600 BLVD S SUITE 208 HUNTSVILLE AL 35802
3	KAMAN SCIENCES CORP S JONES G L PADEREWSKI R G PONZINI 1500 GRDN OF THE GODS RD COLORADO SPRINGS CO 80907
1	D R KENNEDY & ASSOC INC D KENNEDY PO BOX 4003 MOUNTAIN VIEW CA 94040
2	KTECH CORPORATION F W DAVIES L M LEE 901 PENNSYLVANIA NE ALBUQUERQUE NM 87110
1	LIVERMORE SOFTWARE TECH CORP J O HALLQUIST 2876 WAVERLY WAY LIVERMORE CA 94550
1	LOCKHEED MARTIN ELEC & MSLS G W BROOKS 5600 SAND LAKE RD MP 544 ORLANDO FL 32819-8907
1	LOCKHEED MARTIN MISSILE & SPACE W R EBERLE PO BOX 070017 HUNTSVILLE AL 35807
3	LOCKHEED MARTIN MISSILE & SPACE M A LEVIN ORG 81 06 BLDG 598 M R MCHENRY T A NGO ORG 81 10 BLDG 157 111 LOCKHEED WAY SUNNYVALE CA 94088

<u>NO. OF</u> <u>COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF</u> <u>COPIES</u>	<u>ORGANIZATION</u>
4	LOCKHEED MISSILE & SPACE CO J R ANDERSON W C KNUDSON S KUSUMI 0 81 11 BLDG 157 J PHILLIPS 0 54 50 PO BOX 3504 SUNNYVALE CA 94088	1	ROCKWELL INTERNATIONAL ROCKETDYNE DIVISION H LEIFER 16557 PARK LN CIRCLE LOS ANGELES CA 90049
1	LOCKHEED MISSILE & SPACE CO R HOFFMAN SANTA CRUZ FACILITY EMPIRE GRADE RD SANTA CRUZ CA 95060	1	ROCKWELL MISSILE SYS DIV T NEUHART 1800 SATELLITE BLVD DULUTH GA 30136
1	MCDONNELL DOUGLAS ASTRONAUTICS CO B L COOPER 5301 BOLSA AVE HUNTINGTON BEACH CA 92647	1	SAIC M W MCKAY 10260 CAMPUS POINT DR SAN DIEGO CA 92121
1	NETWORK COMPUTING SVCS INC T HOLMQUIST 1200 WASHINGTON AVE S MINNEAPOLIS MN 55415	1	SHOCK TRANSIENTS INC D DAVISON BOX 5357 HOPKINS MN 55343
1	PHYSICAL SCIENCES INC P NEBOLSINE 20 NEW ENGLAND BUS CTR ANDOVER MA 01810	2	SIMULATION & ENG CO INC E I MULLINS S E MULLINS 8840 HWY 20 SUITE 200 N MADISON AL 35758
5	PRIMEX TECHNOLOGIES INC G FRAZIER L GARNETT D OLIVER D TUERPE J COFFENBERRY 2700 MERCED ST SAN LEANDRO CA 94577-0599	1	J STERNBERG 20 ESSEX LN WOODBURY CT 06798
1	PRC INC J ADAMS 5166 POTOMAC DR 103 KING GEORGE VA 22485-5824	2	SOUTHERN RESEARCH INST L A DECKARD D P SEGERS PO BOX 55305 BIRMINGHAM AL 35255-5305
1	RAYTHEON ELECTRONIC SYSTEMS R LLOYD 50 APPLE HILL DRIVE TEWKSBURY MA 01876	5	SRI INTERNATIONAL J D COLTON D CURRAN R KLOOP R L SEAMAN D A SHOCKEY 333 RAVENSWOOD AVE MENLO PARK CA 94025
		2	TELEDYNE BROWN ENGR J W BOOTH M B RICHARDSON PO BOX 070007 MS 50 HUNTSVILLE AL 35807-7007

NO. OF
COPIES ORGANIZATION

1 ZERNOW TECHNICAL SVCS INC
L ZERNOW
425 W BONITA AVE SUITE 208
SAN DIMAS CA 91773

ABERDEEN PROVING GROUND

68 DIR USARL
AMSRL SL B
J SMITH
AMSRL SL BA
R DIBELKA
M RITONDO
W WINNER
AMSRL SL BD
D BELY
R GROTE (5 CPS)
C HUNT
J MORRISSEY
J PLOSKONKA
J POLESNE (5 CPS)
J ROBERTSON
L WILSON
AMSRL SL BE
P KUSS
M MAHAFFEY
R SHNIDMAN
AMSRL WM BC
A ZIELINSKI
AMSRL SL BE
P TANENBAUM
AMSRL WM BE
S L HOWARD
AMSRL WM BD
A J KOTLAR
AMSRL WM MB
G GAZONAS
C HOPPEL
AMSRL WM MC
J M WELLS
AMSRL WM T
T W WRIGHT
AMSRL WM TA
W GILLICH
W BRUCHEY
M BURKINS
W A GOOCH
H W MEYER
J RUNYEON
AMSRL WM TB
R FREY
P BAKER

NO. OF
COPIES ORGANIZATION

ABERDEEN PROVING GROUND

AMSRL WM TB
R LOTTERO
J STARKENBERG
AMSRL WM TC
R COATES
T W BJERKE
K KIMSEY
M LAMPSON
D SCHEFFLER
S SCHRAML
G SILSBY
B SORENSEN
R SUMMERS
W WALTERS
AMSRL WM TD
A M DIETRICH
J COX
D DANDEKAR
K FRANK
M RAFTENBERG
G RANDERS PEHRSON
E J RAPACKI
M SCHEIDLER
S SCHOENFELD
S SEGLETES (5 CPS)
T WEERISOORIYA
AMSRL WM TE
J POWELL
A PRAKASH

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	AERONAUTICAL & MARITIME RESEARCH LABORATORY N BURMAN S CIMPOERU D PAUL PO BOX 4331 MELBOURNE VIC 3001 AUSTRALIA
1	PRB S A M VANSNICK AVE DE TERVUEREN 168 BTE 7 BRUSSELS B 1150 BELGIUM
1	ROYAL MILITARY ACADEMY G DYCKMANS RENAISSANCELAAN 30 1000 BRUSSELS BELGIUM
1	BULGARIAN ACADEMY OF SCI SPACE RESEARCH INSTITUTE V GOSPODINOV 1000 SOFIA PO BOX 799 BULGARIA
1	CANADIAN ARSENALS LTD P PELLETIER 5 MONTEE DES ARSENAUX VILLIE DE GRADEUR PQ J5Z2 CANADA
1	DEFENCE RSCH ESTAB SUFFIELD D MACKAY RALSTON ALBERTA TOJ 2NO RALSTON CANADA
1	DEFENCE RSCH ESTAB SUFFIELD C WEICKERT BOX 4000 MEDICINE HAT ALBERTA T1A 8K6 CANADA
1	DEFENCE RSCH ESTAB VALCARTIER ARMAMENTS DIVISION R DELAGRAVE 2459 PIE X1 BLVD N PO BOX 8800 CORCELETTE QUEBEC GOA 1R0 CANADA

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	CEA R CHERET CEDEX 15 313 33 RUE DE LA FEDRATION PARIS 75752 FRANCE
1	CEA CISI BRANCH P DAVID CENTRE DE SACLAY BP 28 GIF SUR YVETTE 91192 FRANCE
1	CEA CESTA A GEILLE BOX 2 LE BARP 33114 FRANCE
5	CENTRE D'ETUDES DE GRAMAT C LOUPIAS P OUTREBON J CAGNOUX C GALLIC J TRANCHET GRAMAT 46500 FRANCE
3	CENTRE D'ETUDES DE VAUJOURS J P PLOTARD E BOTTET TAT SIHN VONG BOITE POSTALE NO 7 COUNTRY 77181 FRANCE
6	CENTRE DE RECHERCHES ET D'ETUDES D ARCUEIL D BOUVART C COTTENNOT S JONNEAUX H ORSINI S SERROR F TARDIVAL 16 BIS AVENUE PRIEUR DE LA COTE D OR F94114 ARCUEIL CDEX FRANCE

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DAT ETBS CETAM C ALTMAYER ROUTE DE GUERRY BOURGES 18015 FRANCE
1	ETBS DSTI P BARNIER ROUTE DE GUERAY BOITE POSTALE 712 18015 BOURGES CEDEX FRANCE
1	FRENCH GERMAN RSRCH INST P Y CHANTERET CEDEX 12 RUE DE L'INDUSTRIE BP 301 F68301 SAINT LOUIS FRANCE
5	FRENCH GERMAN RSRCH INST H-J ERNST F JAMET P LEHMANN K HOOG H F LEHR CEDEX 5 5 RUE DU GENERAL CASSAGNOU SAINT LOUIS 68301 FRANCE
1	BATTELLE INGENIEUTECHNIK GMBH W FUCHE DUESSELDORFFER STR 9 ESCHBORN D 65760 GERMANY
1	CONDAT J KIERMEIR MAXIMILIANSTR 28 8069 SCHEYERN FERNHAG GERMANY
1	DEUTSCHE AEROSPACE AG M HELD POSTFACH 13 40 D 86523 SCHROBENHAUSEN GERMANY

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIEHL GBMH AND CO M SCHILDKNECHT FISCHBACHSTRASSE 16 D 90552 R(TM)TBENBACH AD PEGNITZ GERMANY
4	ERNST MACH INSTITUT V HOHLER E SCHMOLINSKE E SCHNEIDER K THOMA ECKERSTRASSE 4 D-7800 FREIBURG I BR 791 4 GERMANY
3	FRAUNHOFER INSTITUT FUER KURZZEITDYNAMIK ERNST MACH INSTITUT H ROTHENHAEUSLER H SENF E STRASSBURGER KLINGELBERG 1 D79588 EFRINGEN KIRCHEN GERMANY
2	IABG M BORRMANN H G DORSCH EINSTEINSTRASSE 20 D 8012 OTTOBRUN B MUENCHEN GERMANY
1	INGENIEURBRO DEISENROTH AUF DE HARDT 33 35 D5204 LOHMAR 1 GERMANY
3	TU CHEMNITZ-ZWICKAU I FABER L KRUEGER L MEYER FAKULTAET FUER MASCHINENBAU U VERFAHRENSTECHNIK SCHEFFELSTRASSE 110 09120 CHEMNITZ GERMANY
1	TU MNCHEN E IGENBERGS ARCISSTRASSE 21 8000 MNCHEN 2 GERMANY

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
5	RAFAEL BALLISTICS CNTR E DEKEL Y PARTOM G ROSENBERG Z ROSENBERG Y YESHURUN PO BOX 2250 HAIFA 31021 ISRAEL
1	TECHNION INST OF TECH FACULTY OF MECH ENGNG S BODNER TECHNION CITY HAIFA 32000 ISRAEL
1	IHI RESEARCH INSTITUTE STRUCTURE & STRENGTH T SHIBUE 1 15 TOYOSU 3 KOTO TOKYO 135 JAPAN
1	ESTEC CS D CASWELL BOX 200 NOORDWIJK 2200 AG NETHERLANDS
4	PRINS MAURITS LABORATORY H J REITSMA E VAN RIET H PASMAN R YSSELSTEIN TNO BOX 45 RIJSWIJK 2280AA NETHERLANDS
4	INSTITUTE FOR PROBLEMS IN MECH ENGINEERING RAS V BULATOV D INDEITSEV A KRIVTSOV Y MESCHERYAKOV BOLSHOY PR VO 61 ST PETERSBURG 199178 RUSSIAN REPUBLIC

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	INSTITUTE OF MINEROLOGY & PETROGRAPHY V A DREBUSHCHAK UNIVERSITETSKI PROSPEKT 3 630090 NOVOSIBIRSK RUSSIAN REPUBLIC
1	IPE RAS A A BOGOMAZ DVORTSOVAIA NAB 18 ST PETERSBURG RUSSIAN REPUBLIC
2	LAVRENTYEV INST HYDRODYNAMICS L A MERZHIEVSKY V V SILVESTROV 630090 NOVOSIBIRSK RUSSIAN REPUBLIC
1	RESEARCH INSTITUTE OF MECHANICS NIZHNIY NOVGOROD STATE UNIVERSITY A SADYRIN P R GAYARINA 23 KORP 6 NIZHNIY NOVGOROD 603600 RUSSIAN REPUBLIC
1	SAMARA STATE AEROSPACE UNIVERSITY L G LUKASHEV SAMARA RUSSIAN REPUBLIC
1	TOMSK BRANCH OF THE INSTITUTE FOR STRUCTURAL MACROKINETICS V GORELSKI 8 LENIN SQ GSP 18 TOMSK 634050 RUSSIAN REPUBLIC
1	DYNAMEC RESEARCH AB A PERSSON PO BOX 201 S 151 23 S(TM)DERTLJE SWEDEN

NO. OF
COPIES ORGANIZATION

7 NATL DEFENCE RESEARCH EST
L HOLMBERG
U LINDEBERG
L GUNNAR OLSSON
L HOLMBERG
B JANZON
I MELLGARD
G WIJK
FOA BOX 551
TUMBA S 14725
SWEDEN

2 SWEDISH DEFENCE RSCH ESTAB
DIVISION OF MATERIALS
S J SAVAGE
J ERIKSON
STOCKHOLM S-17290
SWEDEN

2 K&W THUN
W LANZ
W ODERMATT
ALLMENDSSTRASSE 86
CH-3602 THUN
SWITZERLAND

2 AWE
M GERMAN
W HARRISON
FOULNESS ESSEX SS3 9XE
UNITED KINGDOM

2 DERA
I CULLIS
J P CURTIS
FORT HALSTEAD
SEVENOAKS KENT TN14 7BP
UNITED KINGDOM

6 DEFENCE RESEARCH AGENCY
W A J CARSON
I CROUCH
C FREW
T HAWKINS
B JAMES
B SHRUBSALL
CHOBHAM LANE CHERTSEY
SURREY KT16 0EE
UNITED KINGDOM

NO. OF
COPIES ORGANIZATION

1 UK MINISTRY OF DEFENCE
G J CAMBRAY
CBDE PORTON DOWN SALISBURY
WILTSHIRE SPR 0JQ
UNITED KINGDOM

1 INSTITUTE FOR PROBLEMS OF
STRENGTH
G STEPANOV
TIMIRYAZEVS KAYU STR 2
252014 KIEV
UKRAINE

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
<small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small>				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE June 2001		3. REPORT TYPE AND DATES COVERED Reprint, October 2000 – December 2000
4. TITLE AND SUBTITLE Improving the Rod-Penetration Algorithm for Tomorrow's Armors			5. FUNDING NUMBERS AH80	
6. AUTHOR(S) Steven B. Segletes, Rick Grote, and John Polesne				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-TD Aberdeen Proving Ground, MD 21005-5066			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-RP-23	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES A reprint from <i>Proceedings of the 22nd Army Science Conference</i> , pp. 66–71, Baltimore, MD, 11–13 December 2000.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) The performance of the respected Frank-Zook penetration algorithm (Zook, J. A., Frank, K., and Silsby, G. F., "Terminal Ballistics Test and Analysis Guidelines for the Penetration Mechanics Branch," BRL-MR-3960, January 1992) is examined in light of an anticipated class of target technologies involving laminated targets whose layers are thin relative to the projectile diameter. This class of target designs encompasses multifunctional integral armors and, in the limiting case, armors incorporating functionally-graded materials. Such armor classes represent potential candidates for the Army's Future Combat System. The ability to effectively model the ballistic response of advanced armors is paramount to accurately assessing system lethality and vulnerability for future weapon systems and platforms.				
14. SUBJECT TERMS penetration, algorithm, MUVES			15. NUMBER OF PAGES 23	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-RP-23 (Segletes) Date of Report June 2001

2. Date Report Received _____

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)

(DO NOT STAPLE)